



SBR-1502 Polymer Data

Polymerization System : Cold emulsion Polymerization

Emulsifier : Mixed acid soap

Stabilizer : Non-Staining, Non-Discoloring

Coagulant : Acid

Characteristics : Bright colored stock with excellent color stability.

Improved abrasion resistance, flexibility, where excellent physical properties and non-staining

antioxidant are required.

Application : Tires (especially white sidewall), shoe soles and heels, sporting goods, floor covering, industrial

goods (especially light colored goods) and miscellaneous items

	9.0	PECIFICATION VALUES		
POLYMER PROPERTIES	or or	Minimum	Maximum	Test Method
Bound Styrene	(%)	22.5 01	24.5	ASTM D-5775
Volatile Matter	(%)		0.75	ASTM D-5668
Ash	(%)	******	0.75	ASTM D-5667
Organic Acid	(%)	4.75	7.00	ASTM D-5774
Soap	(%)		0.50	ASTM D-5774
Mooney Viscosity, ML, 100°C		46	58	ASTM D-1646
*Massed sample				A STATE OF THE PARTY OF THE PAR
COMPOUND PROPERTIES (Te	est Recipe ASTM D-318	5; Cure @145°C)		
Tensile Strength	35' (kg/cm²)	230	******	ASTM D-412
Elongation	35' (%)	330	*****	ASTM D-412
300% Modulus	25' (kg/cm ²)	130	170	ASTM D-412
	35' (kg/cm³)	160	200	ASTM D-412
	50' (kg/cm²)	175	215	ASTM D-412
Test Recipe, ASTM D-3185	Parts	A CONTRACTOR OF THE PARTY OF TH		Service Control of the
Taipol SBR-1502	100.00			
Zinc oxide	3.00			
Stearic acid	1.00			
Sulfur	1.75			
HAF Black (IRB#7)	50.00			
TBBS	1.00			
Total	156.75			

Limited Warranty

There are no warranties which extend beyond the product description herein, and seller makes no warranty, express or implied, of fitness for particular use, merchantability or otherwise with respect to product, whether used singly or in combination with other substances or in any process, except that product sold hereunder shall conform to seller's standard sales specifications as of the date of the shipment. Without limiting the foregoing, seller does not recommend or endorse the use of product(s) in any medical application and specifically disclaims any representation or warranty, express or implied, of suitability or fitness for use or otherwise, with respect to product(s)' use in any medical application. Buyer represents and warrants that no product(s) purchased hereunder will be used in or resold into any commercial or developmental manner in connection with medical applications without seller's prior express written acknoledgement, further, buyer agrees that it will make no representations, express or implied, to any person to the effect that seller recommends or endorses the use of products(s) purchased hereunder in any medical application.