

SABIC[®] BR 5510

POLYBUTADIENE RUBBER

DESCRIPTION

BR 5510 is a high cis-1,4 Polybutadiene rubber stabilized with a non-staining antioxidant. BR 5510 is manufactured by solution polymerization process using stereo-specific Nickel catalyst system to control microstructure and Molecular weight distribution and provides a highly linear polymer.

TYPICAL PROPERTY VALUES

Revision 20181120

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CHARACTERISTIC			
Appearance	Off-white to light amber	Visual	Visual
POLYMER PROPERTIES			
Mooney viscosity (ML 1+4 @100 °C) ⁽¹⁾	55	MU	ASTM D1646
Volatiles	0.50	% max	ASTM D5668
Organic acid	0.775	%	ASTM D5774
Ash Content ⁽²⁾	0.25	% max	ASTM D5667
Cis 1,4 Content	96	% min	SABIC method

(1) +/-5

(2) Typical values; not to be construed as specification limits.

CHARACTERISTICS

BR 5510 is a high Mooney grade generally used in blend with other elastomers and is designed for: excellent abrasion resistance, excellent flex cracking resistance, excellent resilience, good low temperature properties and low rolling resistance

APPLICATIONS

Tire tread, sidewall and carcass, conveyor belt coverings, shoe sole, hoses and tube covers, mechanical and sporting goods

STORAGE AND HANDLING

BR 5510 is packed in returnable or non-returnable metal crates consisting of 36 bales, weighing approximately 1.26 tons net. The individual bale weighs 35+/-1 kg, and is wrapped in Low-density polyethylene films. The product should be stored in its original packing at ambient temperature in dry conditions away from heat, ultraviolet light and direct sun light. Under suitable storage conditions, the product is stable for 24 months from the date of manufacture. Inappropriate storage conditions may lead to quality deterioration such as color, viscosity change etc. that could result in inadequate product performance.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.