

SABIC[®] FORTIFY[™] C30070D

POLYOLEFIN ELASTOMER

DESCRIPTION

SABIC[®] FORTIFY[™] C30070D is an ethylene octene copolymer produced by solution polymerization using metallocene catalyst. This product is available as free flowing pellets.

SABIC[®] FORTIFY[™] C30070D is designed as a high performance copolymer modifier to provide superior toughness, softness and optical properties. It also provides excellent flow properties.

TYPICAL APPLICATIONS

Impact modifier in thermoplastic olefin compounds, footwear midsoles and wire and cable extrusion.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Density	868	kg/m ³	ASTM D792
Melt Flow Rate			
at 190°C and 2.16 kg	30.0	g/10 min	ASTM D1238
at 230°C and 2.16 kg	70.0	g/10 min	ASTM D1238
Mooney viscosity (ML 1+4, 121 °C)	2	MU	ASTM D1646
MECHANICAL PROPERTIES			
Durometer Hardness			
shore A (1 second)	68	-	ASTM D2240
shore D (1 second)	17	-	ASTM D2240
Flexural Modulus (1% Secant)	10.8	MPa	ASTM D790 A
Tear Strength (Type C)	29.4	kN/m	ASTM D624
FILM PROPERTIES			
Tensile Properties ⁽¹⁾			
strength at break	3.1	MPa	ASTM D638
elongation	>1000	%	ASTM D638
1% secant modulus	10.8	MPa	ASTM D790
100% modulus	1.7	MPa	ASTM D638
THERMAL PROPERTIES			
Peak Melting Temperature	62	°C	SABIC method
Glass Transition Temperature, T _g	-52	°C	SABIC method

(1) All physical properties were measured from specimens cut from compression molded. These typical values depend on manufacturing conditions. Therefore, customers should confirm the product performance by using their own tests.

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, available on the Internet (www.SABIC.com). Additional specific information can be requested via your local Sales Office.

This product is not intended for and must not be used in any pharmaceutical/medical applications

STORAGE AND HANDLING

POE Polyolefin Elastomer resins (in pelletized form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 30 °C. Further avoid temperatures above 50 °C and below 10 °C. Please mind the temperature conditions when using the low density grades <math><0.875 \text{ g/cm}^3</math>, especially when the shipment or storage temperature would approach the softening and melting temperature of the POE resin. Outer package wrap should not be removed from the pallets until the products are ready to be used. Stacking of pallets is not recommended due to dimensional instability and material blocking risk. Grades with D suffix are being treated with anti-caking dust agent to reduce blocking behaviour. It is advisable to process Polyolefin Elastomers resins within 6 months after delivery, this because also excessive aging can lead to a deterioration in quality.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.